

CHIEM PATANA SYNTHETIC FIBERS CO.,LTD.



25/1 M.6, Petkaseam Rd Km.74, Photharam ,Ratchaburi ,70120 ,Thailand.

23/3 M.3, Petkaseam Rd Km.33, Yaicha,Sampran ,Nakornpratom,73110 ,Thailand.

Telephone: (66-34) 311273-4 , Facsimile: (66-34) 322-559

<http://www.chiempatana.com> , E-mail : info@chiempatana.com

SPECIFICATION

DTY 150/48-SDS (Polyester Textured Yarn)

Semi-Dull , Raw White , Double Heat Set , Non-Intermingle

Grade	AA	DATA		Unit
Type	Setting Yarn (SDS)	Setting Yarn (SDS)		----
QUARTER	-----	Q 2	Q 3	----
Denier	152 +/- 5	152.0	152.8	den
Tenacity	4.6 +/- 1	4.8	4.8	g/den
Elongation	25 +/- 5	26.1	25.2	%
Crimp Rigidity	4 +/- 1.5	3.5	3.4	%
Shrinkage in Boiling Water	1.5 +/- 1	1.4	1.5	%
O P U.	1.5 +1.5 , - 0.5	1.5	1.6	%
Torque	2 +/- 1	1.9	1.8	twist/inch.
DTY Diameter	23.5 +/- 0.5	23.5 +/- 0.5		cm
Package (WEIGHT)	5.5	5.5		kgs
Package (BOBBIN)	Full Bobbin	Full Bobbin		---

REMARK : QUARTER 2 , 3 ใ 2549