



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 20/1 COMBED COTTON 100% LOT 1073

Yarn Count	Actual count		19.79	S'
	CV%		0.57	%
Yarn Twist	TPI		15.34	T/inch
	TPM		603.94	T/m
Yarn Evenness	Uster U%		8.98	%
	Thin Places		0.20	/ km
	Thick Places		6.40	/ km
	Neps		12.40	/ km
Yarn Hairiness	H		7.41	%
	CV _b		3.60	%
Yarn Strength	Elongation	average%	5.21	%
		CV%	4.89	%
	Lea Tensile Strength		65	kg/120yd
	Single Yarn Tensile Strength		498	gm
	RKM		16.70	gm/tex
Package Length			89,642	m

Remark

WAXED