



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 24/1 COMBED COTTON 100% LOT 0073

Yarn Count	Actual count	23.84	S'	
	CV%	0.66	%	
Yarn Twist	TPI	15.75	T/inch	
	TPM	620.08	T/m	
Yarn Evenness	Uster U%	8.90	%	
	Thin Places	0.10	/ km	
	Thick Places	8.40	/ km	
	Neps	19.10	/ km	
Yarn Hairiness	H	7.40	%	
	CV _b	2.90	%	
Yarn Strength	Elongation	average%	4.53	%
		CV%	5.15	%
	Lea Tensile Strength	50	kg/120yd	
	Single Yarn Tensile Strength	379	gm	
	RKM	15.30	gm/tex	
Package Length		79,893	m	

Remark

WAXED