



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 30/1 COMBED COTTON 100% LOT 0073A2

Yarn Count	Actual count		29.75	S'
	CV%		0.47	%
Yarn Twist	TPI		19.60	T/inch
	TPM		771.65	T/m
Yarn Evenness	Uster U%		9.86	%
	Thin Places		1.00	/ km
	Thick Places		20.30	/ km
	Neps		47.30	/ km
Yarn Hairiness	H		6.46	%
	CV _b		4.70	%
Yarn Strength	Elongation	average%	4.38	%
		CV%	7.22	%
	Lea Tensile Strength		43	kg/120yd
	Single Yarn Tensile Strength		328	gm
	RKM		16.52	gm/tex
Package Length			131,100	m

Remark

WAXED