

CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4, 322447-8 Fax. (66-34)322559, 225532
<http://www.chiempatana.com>
 E-mail: info@chiempatana.com

SPECIFICATION**NE 32/1 COMBED COTTON 100% LOT 1073**

Yarn Count	Actual count	31.96	S'	
	CV%	0.88	%	
Yarn Twist	TPI	23.11	T/inch	
	TPM	909.84	T/m	
Yarn Evenness	Uster U%	9.85	%	
	Thin Places	0.90	/ km	
	Thick Places	16.00	/ km	
	Neps	45.00	/ km	
Yarn Hairiness	H	4.99	%	
	CV _b	2.80	%	
Yarn Strength	Elongation	average%	4.63	%
		CV%	5.95	%
	Lea Tensile Strength	41	kg/120yd	
	Single Yarn Tensile Strength	315	gm	
	RKM	17.07	gm/tex	
Package Length		140,700	m	

Remark

WAXED