



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 36/2 COMBED COTTON 100% LOT 8061P

Yarn Count	Actual count	17.50	S'	
	CV%	1.92	%	
Yarn Twist	TPI	15.77	T/inch	
	TPM	620.86	T/m	
Yarn Evenness	Uster U%	7.33	%	
	Thin Places	0	/ km	
	Thick Places	0.4	/ km	
	Neps	2.1	/ km	
Yarn Hairiness	H	6.62	%	
	CV <sub>b</sub>	0.40	%	
Yarn Strength	Elongation	average%	5.71	%
		CV%	4.10	%
	Lea Tensile Strength	75	kg/120yd	
	Single Yarn Tensile Strength	597	gm	
	RKM	17.68	gm/tex	
Package Length		59,000	m	

Remark

UNWAXED