



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 40/2 COMBED COTTON 100% LOT 6099

Yarn Count	Actual count	19.68	S'	
	CV%	0.85	%	
Yarn Twist	TPI	17.35	T/inch	
	TPM	683.07	T/m	
Yarn Evenness	Uster U%	7.42	%	
	Thin Places	0	/ km	
	Thick Places	1.3	/ km	
	Neps	3.8	/ km	
Yarn Hairiness	H	6.78	%	
	CV <sub>b</sub>	4.70	%	
Yarn Strength	Elongation	average%	6.74	%
		CV%	4.28	%
	Lea Tensile Strength	72	kg/120yd	
	Single Yarn Tensile Strength	541	gm	
	RKM	18.01	gm/tex	
Package Length		63,500	m	

Remark

UNWAXED