



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 40/1 COMBED COTTON 100% LOT 0073

Yarn Count	Actual count		39.85	S'
	CV%		0.64	%
Yarn Twist	TPI		22.60	T/inch
	TPM		889.76	T/m
Yarn Evenness	Uster U%		10.15	%
	Thin Places		1.70	/ km
	Thick Places		32.20	/ km
	Neps		111.50	/ km
Yarn Hairiness	H		5.85	%
	CV _b		3.30	%
Yarn Strength	Elongation	average%	3.95	%
		CV%	3.55	%
	Lea Tensile Strength		30	kg/120yd
	Single Yarn Tensile Strength		227	gm
	RKM		15.29	gm/tex
Package Length			170,635	m

Remark

WAXED



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 40/1 COMBED COTTON 100% LOT 0073

Yarn Count	Actual count	40.12	S'	
	CV%	0.78	%	
Yarn Twist	TPI	25.75	T/inch	
	TPM	1013.78	T/m	
Yarn Evenness	Uster U%	10.25	%	
	Thin Places	2.40	/ km	
	Thick Places	33.80	/ km	
	Neps	116.30	/ km	
Yarn Hairiness	H	5.20	%	
	CV _b	4.00	%	
Yarn Strength	Elongation	average%	4.18	%
		CV%	6.56	%
	Lea Tensile Strength	32	kg/120yd	
	Single Yarn Tensile Strength	250	gm	
	RKM	17.01	gm/tex	
Package Length		170,285	m	

Remark

UNWAXED