

CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4, 322447-8 Fax. (66-34)322559, 225532
<http://www.chiempatana.com>
 E-mail: info@chiempatana.com

SPECIFICATION**NE 40/1 COMBED COTTON 100% LOT 1073**

Yarn Count	Actual count	39.74	S'	
	CV%	0.84	%	
Yarn Twist	TPI	22.60	T/inch	
	TPM	889.76	T/m	
Yarn Evenness	Uster U%	10.11	%	
	Thin Places	2.00	/ km	
	Thick Places	27.30	/ km	
	Neps	95.00	/ km	
Yarn Hairiness	H	5.65	%	
	CV _b	2.90	%	
Yarn Strength	Elongation	average%	4.29	%
		CV%	6.98	%
	Lea Tensile Strength	30	kg/120yd	
	Single Yarn Tensile Strength	226	gm	
	RKM	15.19	gm/tex	
Package Length		173,770	m	

Remark

WAXED

CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4, 322447-8 Fax. (66-34)322559, 225532
<http://www.chiempatana.com>
 E-mail: info@chiempatana.com

SPECIFICATION**NE 40/1 COMBED COTTON 100% LOT 1073**

Yarn Count	Actual count	39.93	S'	
	CV%	0.81	%	
Yarn Twist	TPI	25.75	T/inch	
	TPM	1013.78	T/m	
Yarn Evenness	Uster U%	10.35	%	
	Thin Places	4.00	/ km	
	Thick Places	28.90	/ km	
	Neps	91.30	/ km	
Yarn Hairiness	H	5.34	%	
	CV _b	3.00	%	
Yarn Strength	Elongation	average%	4.73	%
		CV%	6.73	%
	Lea Tensile Strength	32	kg/120yd	
	Single Yarn Tensile Strength	257	gm	
	RKM	17.35	gm/tex	
Package Length		63,900	m	

Remark

UNWAXED