



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 40/1 PIMA 100% LOT 6099

Yarn Count	Actual count		40.00	S'
	CV%		0.80	%
Yarn Twist	TPI		23.62	T/inch
	TPM		929.92	T/m
Yarn Evenness	Uster U%		9.80	%
	Thin Places		0.8	/ km
	Thick Places		27.1	/ km
	Neps		82.5	/ km
Yarn Hairiness	H		5.00	%
	CV		2.80	%
Yarn Strength	Elongation	average%	4.80	%
		CV%	5.51	%
	Lea Tensile Strength		40	kg/120yd
	Single Yarn Tensile Strength		294	gm
	RKM		19.88	gm/tex
Package Length			118,544	m

Remark WAXED