

CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4, 322447-8 Fax. (66-34)322559, 225532
<http://www.chiempatana.com>
 E-mail: info@chiempatana.com

SPECIFICATION**NE 50/1 COMBED COTTON 100% LOT 1073**

Yarn Count	Actual count		50.12	S'
	CV%		0.85	%
Yarn Twist	TPI		27.86	T/inch
	TPM		1096.85	T/m
Yarn Evenness	Uster U%		10.89	%
	Thin Places		12.70	/ km
	Thick Places		42.60	/ km
	Neps		126.50	/ km
Yarn Hairiness	H		5.03	%
	CV _b		2.20	%
Yarn Strength	Elongation	average%	3.92	%
		CV%	5.34	%
	Lea Tensile Strength		22	kg/120yd
	Single Yarn Tensile Strength		187	gm
	RKM		15.84	gm/tex
Package Length			214,500	m

Remark

WAXED