



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 60/2 COMBED COTTON 100% LOT 6099

Yarn Count	Actual count		30.59	S'
	CV%		1.30	%
Yarn Twist	TPI		25.65	T/inch
	TPM		1009.84	T/m
Yarn Evenness	Uster U%		8.69	%
	Thin Places		0	/ km
	Thick Places		9.2	/ km
	Neps		31.3	/ km
Yarn Hairiness	H		5.65	%
	CV _b		0.70	%
Yarn Strength	Elongation	average%	6.07	%
		CV%	6.89	%
	Lea Tensile Strength		46	kg/120yd
	Single Yarn Tensile Strength		378	gm
	RKM		19.58	gm/tex
Package Length			71,100	m

Remark

UNWAXED