



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 60/1 COMBED COTTON 100% LOT 2023

Yarn Count	Actual count		59.88	S'
	CV%		0.65	%
Yarn Twist	TPI		34.50	T/inch
	TPM		1358.27	T/m
Yarn Evenness	Uster U%		12.19	%
	Thin Places		61.40	/ km
	Thick Places		105.40	/ km
	Neps		271.80	/ km
Yarn Hairiness	H		4.35	%
	CV <sub>b</sub>		1.30	%
Yarn Strength	Elongation	average%	3.55	%
		CV%	5.56	%
	Lea Tensile Strength		19	kg/120yd
	Single Yarn Tensile Strength		166	gm
	RKM		16.85	gm/tex
Package Length			192,500	m

Remark

WAXED