



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 60/1 PIMA 50% / COMBED COTTON 50% LOT 6099

Yarn Count	Actual count	60.06	S'	
	CV%	0.97	%	
Yarn Twist	TPI	33.54	T/inch	
	TPM	1320.47	T/m	
Yarn Evenness	Uster U%	12.07	%	
	Thin Places	30.8	/ km	
	Thick Places	144.6	/ km	
	Neps	249.2	/ km	
Yarn Hairiness	H	4.33	%	
	CV	4.20	%	
Yarn Strength	Elongation	average%	5.24	%
		CV%	6.83	%
	Lea Tensile Strength	21	kg/120yd	
	Single Yarn Tensile Strength	167	gm	
	RKM	16.95	gm/tex	
Package Length		181,880	m	

Remark WAXED