



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 14/1 COMBED COTTON 55% / POLYESTER 45% LOT 1089Q

Yarn Count	Actual count		13.82	S'
	CV%		0.20	%
Yarn Twist	TPI		12.66	T/inch
	TPM		498.42	T/m
Yarn Evenness	Uster U%		7.25	%
	Thin Places		0	/ km
	Thick Places		2.5	/ km
	Neps		10.4	/ km
Yarn Hairiness	H		8.76	%
	CV _b		2.30	%
Yarn Strength	Elongation	average%	9.63	%
		CV%	6.59	%
	Lea Tensile Strength		123	kg/120yd
	Single Yarn Tensile Strength		855	gm
	RKM		20.01	gm/tex
Package Length			47,500	m

Remark

UNWAXED