

CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4, 322447-8 Fax. (66-34)322559, 225532
<http://www.chiempatana.com>
 E-mail: info@chiempatana.com

SPECIFICATION**NE 20/1 COMBED COTTON 60% / POLYESTER 40%**

Yarn Count	Actual count		19.70	S'
	CV%		1.20	%
Yarn Twist	TPI		14.42	T/inch
	TPM		567.72	T/m
Yarn Evenness	Uster U%		8.70	%
	Thin Places		0	/ km
	Thick Places		13.2	/ km
	Neps		30	/ km
Yarn Hairiness	H		7.16	%
	CV _b		2.90	%
Yarn Strength	Elongation	average%	7.10	%
		CV%	7.40	%
	Lea Tensile Strength		79	kg/120yd
	Single Yarn Tensile Strength		601	gm
	RKM		20.04	gm/tex
Package Length			63,900	m

Remark

WAXED