



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 20/1 COMBED COTTON 60% / POLYESTER 40%

Yarn Count	Actual count	19.70	S'	
	CV%	1.20	%	
Yarn Twist	TPI	14.42	T/inch	
	TPM	567.72	T/m	
Yarn Evenness	Uster U%	8.70	%	
	Thin Places	0	/ km	
	Thick Places	13.2	/ km	
	Neps	30	/ km	
Yarn Hairiness	H	7.16	%	
	CV <sub>b</sub>	2.90	%	
Yarn Strength	Elongation	average%	7.10	%
		CV%	7.40	%
	Lea Tensile Strength	79	kg/120yd	
	Single Yarn Tensile Strength	601	gm	
	RKM	20.04	gm/tex	
Package Length		63,900	m	

Remark

WAXED