



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 24/1 COMBED COTTON 55% / POLYESTER 45%

Yarn Count	Actual count	23.70	S'	
	CV%	1.40	%	
Yarn Twist	TPI	14.85	T/inch	
	TPM	584.64	T/m	
Yarn Evenness	Uster U%	9.18	%	
	Thin Places	0.1	/ km	
	Thick Places	21.1	/ km	
	Neps	45.9	/ km	
Yarn Hairiness	H	6.75	%	
	CV _b	3.30	%	
Yarn Strength	Elongation	average%	7.10	%
		CV%	6.40	%
	Lea Tensile Strength	64	kg/120yd	
	Single Yarn Tensile Strength	473	gm	
	RKM	18.98	gm/tex	
Package Length		75,000	m	

Remark

WAXED