

CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION**NE 30/1 COMBED COTTON 55% / POLYESTER 45%**

Yarn Count	Actual count	30.10	S'	
	CV%	1.30	%	
Yarn Twist	TPI	17.5	T/inch	
	TPM	688.98	T/m	
Yarn Evenness	Uster U%	9.97	%	
	Thin Places	0.6	/ km	
	Thick Places	28	/ km	
	Neps	74.9	/ km	
Yarn Hairiness	H	6.27	%	
	CV _b	2.10	%	
Yarn Strength	Elongation	average%	6.60	%
		CV%	7.90	%
	Lea Tensile Strength	48	kg/120yd	
	Single Yarn Tensile Strength	367	gm	
	RKM	18.70	gm/tex	
Package Length		108,300	m	

Remark

WAXED