



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 30/1 COMBED COTTON 55% / POLYESTER 45% LOT 1089Q

Yarn Count	Actual count		29.83	S'
	CV%		1.25	%
Yarn Twist	TPI		17.02	T/inch
	TPM		670.08	T/m
Yarn Evenness	Uster U%		9.85	%
	Thin Places		0.8	/ km
	Thick Places		34.2	/ km
	Neps		74.2	/ km
Yarn Hairiness	H		6.58	%
	CV <sub>b</sub>		2.10	%
Yarn Strength	Elongation	average%	8.49	%
		CV%	8.22	%
	Lea Tensile Strength		49	kg/120yd
	Single Yarn Tensile Strength		359	gm
	RKM		18.12	gm/tex
Package Length			109,500	m

Remark

WAXED