



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 36/1 COMBED COTTON 55% / POLYESTER 45% LOT 1089Q

Yarn Count	Actual count		35.92	S'
	CV%		0.68	%
Yarn Twist	TPI		19.59	T/inch
	TPM		771.26	T/m
Yarn Evenness	Uster U%		10.56	%
	Thin Places		4.2	/ km
	Thick Places		50	/ km
	Neps		92.9	/ km
Yarn Hairiness	H		6.15	%
	CV <sub>b</sub>		2.10	%
Yarn Strength	Elongation	average%	7.85	%
		CV%	7.09	%
	Lea Tensile Strength		40	kg/120yd
	Single Yarn Tensile Strength		291	gm
	RKM		17.67	gm/tex
Package Length			117,000	m

Remark

WAXED