



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 36/1 COMBED COTTON 55% / POLYESTER 45%

Yarn Count	Actual count	36.10	S'	
	CV%	1.40	%	
Yarn Twist	TPI	19.6	T/inch	
	TPM	771.65	T/m	
Yarn Evenness	Uster U%	10.41	%	
	Thin Places	4.6	/ km	
	Thick Places	45	/ km	
	Neps	109.6	/ km	
Yarn Hairiness	H	5.70	%	
	CV <sub>b</sub>	2.90	%	
Yarn Strength	Elongation	average%	6.20	%
		CV%	6.70	%
	Lea Tensile Strength	39	kg/120yd	
	Single Yarn Tensile Strength	308	gm	
	RKM	18.82	gm/tex	
Package Length		116,700	m	

Remark

WAXED