



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 38/1 COMBED COTTON 55% / POLYESTER 45% LOT 1089Q

Yarn Count	Actual count	37.58	S'	
	CV%	1.04	%	
Yarn Twist	TPI	20.77	T/inch	
	TPM	817.71	T/m	
Yarn Evenness	Uster U%	10.58	%	
	Thin Places	3.8	/ km	
	Thick Places	41.7	/ km	
	Neps	93.3	/ km	
Yarn Hairiness	H	5.86	%	
	CV _b	1.30	%	
Yarn Strength	Elongation	average%	7.58	%
		CV%	7.87	%
	Lea Tensile Strength	38	kg/120yd	
	Single Yarn Tensile Strength	276	gm	
	RKM	17.58	gm/tex	
Package Length		125,200	m	

Remark

WAXED