



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 40/2 COMBED COTTON 55% / POLYESTER 45% LOT 1089Q

Yarn Count	Actual count	19.86	S'	
	CV%	1.44	%	
Yarn Twist	TPI	17.88	T/inch	
	TPM	703.94	T/m	
Yarn Evenness	Uster U%	8.01	%	
	Thin Places	0	/ km	
	Thick Places	7.5	/ km	
	Neps	10.4	/ km	
Yarn Hairiness	H	7.30	%	
	CV _b	0.60	%	
Yarn Strength	Elongation	average%	8.59	%
		CV%	6.99	%
	Lea Tensile Strength	82	kg/120yd	
	Single Yarn Tensile Strength	605	gm	
	RKM	20.35	gm/tex	
Package Length		71,600	m	

Remark

UNWAXED