



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 40/1 COMBED COTTON 55% / POLYESTER 45% LOT 1089Q

Yarn Count	Actual count		39.76	S'
	CV%		1.20	%
Yarn Twist	TPI		20.77	T/inch
	TPM		817.71	T/m
Yarn Evenness	Uster U%		10.96	%
	Thin Places		6.3	/ km
	Thick Places		63.3	/ km
	Neps		116.7	/ km
Yarn Hairiness	H		5.77	%
	CV <sub>b</sub>		1.40	%
Yarn Strength	Elongation	average%	7.03	%
		CV%	9.78	%
	Lea Tensile Strength		35	kg/120yd
	Single Yarn Tensile Strength		258	gm
	RKM		17.40	gm/tex
Package Length			148,000	m

Remark

WAXED



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 40/1 COMBED COTTON 55% / POLYESTER 45% LOT 1089Q

Yarn Count	Actual count		39.56	S'
	CV%		0.89	%
Yarn Twist	TPI		24.72	T/inch
	TPM		973.23	T/m
Yarn Evenness	Uster U%		10.74	%
	Thin Places		5.4	/ km
	Thick Places		60	/ km
	Neps		122.1	/ km
Yarn Hairiness	H		5.16	%
	CV <sub>b</sub>		1.30	%
Yarn Strength	Elongation	average%	7.55	%
		CV%	5.64	%
	Lea Tensile Strength		37	kg/120yd
	Single Yarn Tensile Strength		277	gm
	RKM		18.57	gm/tex
Package Length			142,500	m

Remark

UNWAXED