



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 45.5/1 COMBED COTTON 55% / POLYESTER 45% LOT 1089Q

Yarn Count	Actual count	45.26	S'	
	CV%	0.52	%	
Yarn Twist	TPI	23.07	T/inch	
	TPM	908.27	T/m	
Yarn Evenness	Uster U%	11.51	%	
	Thin Places	18.3	/ km	
	Thick Places	106.7	/ km	
	Neps	157.9	/ km	
Yarn Hairiness	H	5.60	%	
	CV <sub>b</sub>	2.10	%	
Yarn Strength	Elongation	average%	7.44	%
		CV%	10.39	%
	Lea Tensile Strength	29	kg/120yd	
	Single Yarn Tensile Strength	234	gm	
	RKM	17.94	gm/tex	
Package Length		162,000	m	

Remark

UNWAXED