

CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION**NE 50/1 COMBED COTTON 60% / POLYESTER 40%**

Yarn Count	Actual count		49.60	S'
	CV%		1.80	%
Yarn Twist	TPI		23.91	T/inch
	TPM		941.34	T/m
Yarn Evenness	Uster U%		11.73	%
	Thin Places		17	/ km
	Thick Places		111	/ km
	Neps		197	/ km
Yarn Hairiness	H		5.34	%
	CV _b		1.80	%
Yarn Strength	Elongation	average%	5.30	%
		CV%	12.20	%
	Lea Tensile Strength		25	kg/120yd
	Single Yarn Tensile Strength		202	gm
	RKM		16.96	gm/tex
Package Length			155,000	m

Remark

WAXED