



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

O/E C 10/1 COTTON 100% LOT 7070R

Yarn Count	Actual count	9.72	S'	
	CV%	1.39	%	
Yarn Twist	TPI	16.50	T/inch	
	TPM	649.61	T/m	
Yarn Evenness	Uster U%	10.86	%	
	Thin Places	2.3	/ km	
	Thick Places	34.8	/ km	
	Neps	279.2	/ km	
Yarn Hairiness	H	8.91	%	
	CV _b	7.80	%	
Yarn Strength	Elongation	average%	6.68	%
		CV%	9.80	%
	Lea Tensile Strength	83	kg/120yd	
	Single Yarn Tensile Strength	588	gm	
	RKM	9.67	gm/tex	
Package Length		38,948	m	

Remark

UNWAXED