



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

O/E C 10/1 COTTON 100% LOT 7070R

Yarn Count	Actual count		9.72	S'
	CV%		1.39	%
Yarn Twist	TPI		16.50	T/inch
	TPM		649.61	T/m
Yarn Evenness	Uster U%		10.86	%
	Thin Places		2.3	/ km
	Thick Places		34.8	/ km
	Neps		279.2	/ km
Yarn Hairiness	H		8.91	%
	CV _b		7.80	%
Yarn Strength	Elongation	average%	6.68	%
		CV%	9.80	%
	Lea Tensile Strength		83	kg/120yd
	Single Yarn Tensile Strength		588	gm
	RKM		9.67	gm/tex
Package Length			38,948	m

Remark

UNWAXED