



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

O/E C 7/1 COTTON 100% LOT 70201R

Yarn Count	Actual count	7.05	S'	
	CV%	1.29	%	
Yarn Twist	TPI	12.00	T/inch	
	TPM	472.44	T/m	
Yarn Evenness	Uster U%	12.12	%	
	Thin Places	3.6	/ km	
	Thick Places	140.7	/ km	
	Neps	386.1	/ km	
Yarn Hairiness	H	9.17	%	
	CV _b	6.30	%	
Yarn Strength	Elongation	average%	7.15	%
		CV%	10.16	%
	Lea Tensile Strength	104	kg/120yd	
	Single Yarn Tensile Strength	752	gm	
	RKM	8.97	gm/tex	
Package Length		29,634	m	

Remark

UNWAXED