



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

O/E R 30/1 RAYON 100% LOT 70694

Yarn Count	Actual count		29.96	S'
	CV%		1.59	%
Yarn Twist	TPI		23.00	T/inch
	TPM		905.51	T/m
Yarn Evenness	Uster U%		11.02	%
	Thin Places		7.1	/ km
	Thick Places		42.1	/ km
	Neps		110	/ km
Yarn Hairiness	H		4.34	%
	CV _b		1.40	%
Yarn Strength	Elongation	average%	10.76	%
		CV%	9.45	%
	Lea Tensile Strength		24	kg/120yd
	Single Yarn Tensile Strength		208	gm
	RKM		10.57	gm/tex
Package Length		115,175	m	

Remark