



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 20/1 POLYESTER 65% / COMBED COTTON 35% LOT 3030P1

Yarn Count	Actual count	19.91	S'	
	CV%	0.65	%	
Yarn Twist	TPI	13.48	T/inch	
	TPM	530.71	T/m	
Yarn Evenness	Uster U%	8.26	%	
	Thin Places	0	/ km	
	Thick Places	9.2	/ km	
	Neps	35	/ km	
Yarn Hairiness	H	7.77	%	
	CV _b	3.30	%	
Yarn Strength	Elongation	average%	9.74	%
		CV%	6.95	%
	Lea Tensile Strength	91	kg/120yd	
	Single Yarn Tensile Strength	725	gm	
	RKM	24.43	gm/tex	
Package Length		71,500	m	

Remark

WAXED