



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 24/1 POLYESTER 65% / COMBED COTTON 35% LOT 3030P1

Yarn Count	Actual count	24.28	S'	
	CV%	1.04	%	
Yarn Twist	TPI	13.66	T/inch	
	TPM	537.79	T/m	
Yarn Evenness	Uster U%	8.75	%	
	Thin Places	0	/ km	
	Thick Places	12.1	/ km	
	Neps	40.4	/ km	
Yarn Hairiness	H	7.33	%	
	CV <sub>b</sub>	2.00	%	
Yarn Strength	Elongation	average%	9.54	%
		CV%	4.85	%
	Lea Tensile Strength	71	kg/120yd	
	Single Yarn Tensile Strength	557	gm	
	RKM	22.90	gm/tex	
Package Length		92,000	m	

Remark

WAXED



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 24/1 POLYESTER 65% / COMBED COTTON 35% LOT 3030P1

Yarn Count	Actual count	23.97	S'	
	CV%	0.79	%	
Yarn Twist	TPI	14.62	T/inch	
	TPM	575.59	T/m	
Yarn Evenness	Uster U%	8.80	%	
	Thin Places	0	/ km	
	Thick Places	10.4	/ km	
	Neps	42.1	/ km	
Yarn Hairiness	H	7.08	%	
	CV <sub>b</sub>	1.80	%	
Yarn Strength	Elongation	average%	9.86	%
		CV%	6.23	%
	Lea Tensile Strength	69	kg/120yd	
	Single Yarn Tensile Strength	571	gm	
	RKM	23.17	gm/tex	
Package Length		82,000	m	

Remark

UNWAXED