



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 30/1 POLYESTER 65% / COMBED COTTON 35% LOT 3030P1

Yarn Count	Actual count	30.16	S'	
	CV%	1.41	%	
Yarn Twist	TPI	16.22	T/inch	
	TPM	638.58	T/m	
Yarn Evenness	Uster U%	9.57	%	
	Thin Places	0	/ km	
	Thick Places	20.8	/ km	
	Neps	83.3	/ km	
Yarn Hairiness	H	6.21	%	
	CV _b	0.80	%	
Yarn Strength	Elongation	average%	9.25	%
		CV%	8.25	%
	Lea Tensile Strength	52	kg/120yd	
	Single Yarn Tensile Strength	430	gm	
	RKM	21.98	gm/tex	
Package Length		102,800	m	

Remark

WAXED



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 30/1 POLYESTER 65% / COMBED COTTON 35% LOT 3030P1

Yarn Count	Actual count	29.95	S'	
	CV%	1.37	%	
Yarn Twist	TPI	17.6	T/inch	
	TPM	692.91	T/m	
Yarn Evenness	Uster U%	9.76	%	
	Thin Places	2.5	/ km	
	Thick Places	22.9	/ km	
	Neps	93.3	/ km	
Yarn Hairiness	H	6.25	%	
	CV _b	2.70	%	
Yarn Strength	Elongation	average%	9.22	%
		CV%	10.24	%
	Lea Tensile Strength	52	kg/120yd	
	Single Yarn Tensile Strength	450	gm	
	RKM	22.81	gm/tex	
Package Length		107,200	m	

Remark

UNWAXED