



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 32/1 POLYESTER 65% / COMBED COTTON 35% LOT 3030P2

Yarn Count	Actual count	32.16	S'	
	CV%	0.62	%	
Yarn Twist	TPI	17.02	T/inch	
	TPM	670.08	T/m	
Yarn Evenness	Uster U%	10.23	%	
	Thin Places	3.3	/ km	
	Thick Places	37.1	/ km	
	Neps	96.7	/ km	
Yarn Hairiness	H	6.14	%	
	CV _b	1.90	%	
Yarn Strength	Elongation	average%	9.45	%
		CV%	6.99	%
	Lea Tensile Strength	52	kg/120yd	
	Single Yarn Tensile Strength	404	gm	
	RKM	22.02	gm/tex	
Package Length		152,000	m	

Remark

WAXED



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 32/1 POLYESTER 65% / COMBED COTTON 35% LOT 3030P2

Yarn Count	Actual count	31.82	S'	
	CV%	1.35	%	
Yarn Twist	TPI	18.54	T/inch	
	TPM	729.92	T/m	
Yarn Evenness	Uster U%	10.08	%	
	Thin Places	2.1	/ km	
	Thick Places	29.2	/ km	
	Neps	97.1	/ km	
Yarn Hairiness	H	5.85	%	
	CV _b	3.20	%	
Yarn Strength	Elongation	average%	9.07	%
		CV%	5.32	%
	Lea Tensile Strength	51	kg/120yd	
	Single Yarn Tensile Strength	408	gm	
	RKM	22.00	gm/tex	
Package Length		146,600	m	

Remark

UNWAXED