

**CHIEM PATANA TEXTILES CO.,LTD.**

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4, 322447-8 Fax. (66-34)322559, 225532  
<http://www.chiempatana.com>  
 E-mail: [info@chiempatana.com](mailto:info@chiempatana.com)

**SPECIFICATION**

**NE 34/2      POLYESTER 65% / COMBED COTTON 35%      LOT 00910**

Yarn Count	Actual count	16.93	S'	
	CV%	0.69	%	
Yarn Twist	TPI	14.96	T/inch	
	TPM	588.98	T/m	
Yarn Evenness	Uster U%	7.52	%	
	Thin Places	0	/ km	
	Thick Places	3.3	/ km	
	Neps	8.8	/ km	
Yarn Hairiness	H	8.26	%	
	CV <sub>b</sub>	4.40	%	
Yarn Strength	Elongation	average%	12.67	%
		CV%	4.00	%
	Lea Tensile Strength	124	kg/120yd	
	Single Yarn Tensile Strength	956	gm	
	RKM	27.41	gm/tex	
Package Length		57,200	m	

Remark

UNWAXED