



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 34/1 POLYESTER 65% / COMBED COTTON 35% LOT 3030P1

Yarn Count	Actual count	33.97	S'	
	CV%	1.35	%	
Yarn Twist	TPI	17.02	T/inch	
	TPM	670.08	T/m	
Yarn Evenness	Uster U%	10.49	%	
	Thin Places	3.3	/ km	
	Thick Places	38.8	/ km	
	Neps	100.8	/ km	
Yarn Hairiness	H	6.39	%	
	CV _b	3.90	%	
Yarn Strength	Elongation	average%	8.89	%
		CV%	6.02	%
	Lea Tensile Strength	45	kg/120yd	
	Single Yarn Tensile Strength	392	gm	
	RKM	22.54	gm/tex	
Package Length		131,500	m	

Remark

WAXED