



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 34/1 POLYESTER 65% / COMBED COTTON 35% LOT 1022N

Yarn Count	Actual count	33.99	S'	
	CV%	0.61	%	
Yarn Twist	TPI	18.44	T/inch	
	TPM	725.98	T/m	
Yarn Evenness	Uster U%	10.28	%	
	Thin Places	4.3	/ km	
	Thick Places	18	/ km	
	Neps	55.7	/ km	
Yarn Hairiness	H	5.58	%	
	CV _b	2.30	%	
Yarn Strength	Elongation	average%	9.25	%
		CV%	10.45	48
	Lea Tensile Strength	49	kg/120yd	
	Single Yarn Tensile Strength	388	gm	
	RKM	22.32	gm/tex	
Package Length		120,000	m	

Remark

UNWAXED