



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

**NE 36/1      POLYESTER 65% / COMBED COTTON 35%      LOT 3030PD**

Yarn Count	Actual count	35.86	S'	
	CV%	1.20	%	
Yarn Twist	TPI	17.60	T/inch	
	TPM	692.91	T/m	
Yarn Evenness	Uster U%	10.62	%	
	Thin Places	5.8	/ km	
	Thick Places	59.2	/ km	
	Neps	121.3	/ km	
Yarn Hairiness	H	6.08	%	
	CV <sub>h</sub>	2.80	%	
Yarn Strength	Elongation	average%	8.89	%
		CV%	7.03	%
	Lea Tensile Strength	42	kg/120yd	
	Single Yarn Tensile Strength	349	gm	
	RKM	21.18	gm/tex	
Package Length		137,000	m	

Remark      WAXED