



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 40/2 POLYESTER 65% / COMBED COTTON 35% LOT 3059Q1

Yarn Count	Actual count	19.96	S'	
	CV%	1.09	%	
Yarn Twist	TPI	16.31	T/inch	
	TPM	642.12	T/m	
Yarn Evenness	Uster U%	7.55	%	
	Thin Places	0	/ km	
	Thick Places	2.5	/ km	
	Neps	8.8	/ km	
Yarn Hairiness	H	7.00	%	
	CV _b	0.60	%	
Yarn Strength	Elongation	average%	10.85	%
		CV%	4.90	%
	Lea Tensile Strength	97	kg/120yd	
	Single Yarn Tensile Strength	772	gm	
	RKM	26.10	gm/tex	
Package Length		59,300	m	

Remark

UNWAXED