



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

**NE 40/1      POLYESTER 65% / COMBED COTTON 35%      LOT 3030PA**

Yarn Count	Actual count	40.22	S'	
	CV%	0.86	%	
Yarn Twist	TPI	19.23	T/inch	
	TPM	757.09	T/m	
Yarn Evenness	Uster U%	10.55	%	
	Thin Places	5.4	/ km	
	Thick Places	45	/ km	
	Neps	124.6	/ km	
Yarn Hairiness	H	5.81	%	
	CV <sub>h</sub>	1.80	%	
Yarn Strength	Elongation	average%	8.20	%
		CV%	8.05	%
	Lea Tensile Strength	39	kg/120yd	
	Single Yarn Tensile Strength	306	gm	
	RKM	20.82	gm/tex	
Package Length		154,000	m	

Remark      WAXED



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

**NE 40/1      POLYESTER 65% / COMBED COTTON 35%      LOT 3030PA**

Yarn Count	Actual count	40.13	S'	
	CV%	1.38	%	
Yarn Twist	TPI	21.19	T/inch	
	TPM	834.25	T/m	
Yarn Evenness	Uster U%	10.50	%	
	Thin Places	4.2	/ km	
	Thick Places	47.5	/ km	
	Neps	117.9	/ km	
Yarn Hairiness	H	5.26	%	
	CV <sub>h</sub>	1.60	%	
Yarn Strength	Elongation	average%	8.72	%
		CV%	6.81	%
	Lea Tensile Strength	41	kg/120yd	
	Single Yarn Tensile Strength	324	gm	
	RKM	22.01	gm/tex	
Package Length		144,000	m	

Remark      UNWAXED