



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 45/2 POLYESTER 65% / COMBED COTTON 35% LOT 3081M4

Yarn Count	Actual count	22.99	S'	
	CV%	0.96	%	
Yarn Twist	TPI	19.08	T/inch	
	TPM	751.18	T/m	
Yarn Evenness	Uster U%	8.14	%	
	Thin Places	0	/ km	
	Thick Places	2.9	/ km	
	Neps	15.8	/ km	
Yarn Hairiness	H	6.50	%	
	CV _b	0.70	%	
Yarn Strength	Elongation	average%	9.47	%
		CV%	5.08	%
	Lea Tensile Strength	87	kg/120yd	
	Single Yarn Tensile Strength	678	gm	
	RKM	26.38	gm/tex	
Package Length		57,200	m	

Remark

UNWAXED