



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 45/1 POLYESTER 65% / COMBED COTTON 35% LOT 1022N

Yarn Count	Actual count	45.06	S'	
	CV%	1.26	%	
Yarn Twist	TPI	22.69	T/inch	
	TPM	893.31	T/m	
Yarn Evenness	Uster U%	11.42	%	
	Thin Places	22.4	/ km	
	Thick Places	57.4	/ km	
	Neps	85.8	/ km	
Yarn Hairiness	H	4.86	%	
	CV _b	3.00	%	
Yarn Strength	Elongation	average%	7.24	%
		CV%	10.30	%
	Lea Tensile Strength	36	kg/120yd	
	Single Yarn Tensile Strength	297	gm	
	RKM	22.05	gm/tex	
Package Length		158,000	m	

Remark

UNWAXED