



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 45/1 POLYESTER 65% / COMBED COTTON 35% LOT 3030PB

Yarn Count	Actual count	45.16	S'	
	CV%	1.32	%	
Yarn Twist	TPI	20.36	T/inch	
	TPM	801.57	T/m	
Yarn Evenness	Uster U%	11.64	%	
	Thin Places	25.8	/ km	
	Thick Places	109.2	/ km	
	Neps	158.8	/ km	
Yarn Hairiness	H	5.83	%	
	CV _h	1.90	%	
Yarn Strength	Elongation	average%	8.09	%
		CV%	8.21	%
	Lea Tensile Strength	32	kg/120yd	
	Single Yarn Tensile Strength	274	gm	
	RKM	20.94	gm/tex	
Package Length		148,000	m	

Remark WAXED



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 45.5/1 POLYESTER 65% / COMBED COTTON 35% LOT 3030PC

Yarn Count	Actual count	45.45	S'	
	CV%	1.23	%	
Yarn Twist	TPI	22.57	T/inch	
	TPM	888.58	T/m	
Yarn Evenness	Uster U%	11.11	%	
	Thin Places	14.2	/ km	
	Thick Places	72.5	/ km	
	Neps	153.3	/ km	
Yarn Hairiness	H	5.01	%	
	CV _h	1.10	%	
Yarn Strength	Elongation	average%	8.57	%
		CV%	8.66	%
	Lea Tensile Strength	32	kg/120yd	
	Single Yarn Tensile Strength	291	gm	
	RKM	22.41	gm/tex	
Package Length		166,000	m	

Remark UNWAXED