



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

**NE 50.5/1 POLYESTER 65% / COMBED COTTON 35% LOT 3030PC**

|                |                              |          |          |   |
|----------------|------------------------------|----------|----------|---|
| Yarn Count     | Actual count                 | 50.53    | S'       |   |
|                | CV%                          | 1.90     | %        |   |
| Yarn Twist     | TPI                          | 34.61    | T/inch   |   |
|                | TPM                          | 1362.60  | T/m      |   |
| Yarn Evenness  | Uster U%                     | 11.78    | %        |   |
|                | Thin Places                  | 33.3     | / km     |   |
|                | Thick Places                 | 131.7    | / km     |   |
|                | Neps                         | 239.6    | / km     |   |
| Yarn Hairiness | H                            | 4.04     | %        |   |
|                | CV <sub>h</sub>              | 1.70     | %        |   |
| Yarn Strength  | Elongation                   | average% | 8.98     | % |
|                |                              | CV%      | 9.80     | % |
|                | Lea Tensile Strength         | 26       | kg/120yd |   |
|                | Single Yarn Tensile Strength | 247      | gm       |   |
|                | RKM                          | 21.09    | gm/tex   |   |
| Package Length |                              | 184,700  | m        |   |

Remark UNWAXED

.....  
 Quality

...../...../.....

.....  
 Manager

...../...../.....