



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 50/1 POLYESTER 65% / COMBED COTTON 35% LOT 3081M4

Yarn Count	Actual count	50.78	S'	
	CV%	1.17	%	
Yarn Twist	TPI	26.62	T/inch	
	TPM	1048.03	T/m	
Yarn Evenness	Uster U%	11.74	%	
	Thin Places	27.1	/ km	
	Thick Places	116.7	/ km	
	Neps	211.3	/ km	
Yarn Hairiness	H	4.46	%	
	CV _h	1.20	%	
Yarn Strength	Elongation	average%	8.82	%
		CV%	7.30	%
	Lea Tensile Strength	29	kg/120yd	
	Single Yarn Tensile Strength	262	gm	
	RKM	22.52	gm/tex	
Package Length		184,700	m	

Remark UNWAXED