



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road.KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 85/1 POLYESTER 65% / COMBED COTTON 35% LOT 4061N

Yarn Count	Actual count	84.97	S'	
	CV%	0.41	%	
Yarn Twist	TPI	36.73	T/inch	
	TPM	1446.06	T/m	
Yarn Evenness	Uster U%	15.25	%	
	Thin Places	610.8	/ km	
	Thick Places	540.8	/ km	
	Neps	685	/ km	
Yarn Hairiness	H	3.68	%	
	CV _b	1.20	%	
Yarn Strength	Elongation	average%	6.86	%
		CV%	12.89	%
	Lea Tensile Strength	12	kg/120yd	
	Single Yarn Tensile Strength	134	gm	
	RKM	19.22	gm/tex	
Package Length		68,000	m	

Remark UNWAXED