



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

RJS NE 24/1 POLYESTER 65% / COMBED COTTON 35% LOT 4050P

Yarn Count	Actual count	23.86	S'	
	CV%	0.74	%	
Yarn Twist	TPI	-	T/inch	
	TPM	-	T/m	
Yarn Evenness	Uster U%	8.9	%	
	Thin Places	0	/ km	
	Thick Places	10	/ km	
	Neps	22.5	/ km	
Yarn Hairiness	H	3.82	%	
	CV _b	1.40	%	
Yarn Strength	Elongation	average%	8.33	%
		CV%	5.57	%
	Lea Tensile Strength	53	kg/120yd	
	Single Yarn Tensile Strength	393	gm	
	RKM	15.87	gm/tex	
Package Length		69,500	m	

Remark WAXED