



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### RJS NE 34/1 POLYESTER 65% / COMBED COTTON 35% LOT 4050P

Yarn Count	Actual count	33.79	S'	
	CV%	1.69	%	
Yarn Twist	TPI	-	T/inch	
	TPM	-	T/m	
Yarn Evenness	Uster U%	10.33	%	
	Thin Places	3.3	/ km	
	Thick Places	30	/ km	
	Neps	104.2	/ km	
Yarn Hairiness	H	3.37	%	
	CV <sub>b</sub>	0.90	%	
Yarn Strength	Elongation	average%	7.16	%
		CV%	7.29	%
	Lea Tensile Strength	37	kg/120yd	
	Single Yarn Tensile Strength	282	gm	
	RKM	16.14	gm/tex	
Package Length		98,500	m	

Remark            WAXED