



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

RJS NE 45/1 POLYESTER 65% / COMBED COTTON 35% LOT 4050P

Yarn Count	Actual count	44.76	S'	
	CV%	0.99	%	
Yarn Twist	TPI	-	T/inch	
	TPM	-	T/m	
Yarn Evenness	Uster U%	11.81	%	
	Thin Places	29.6	/ km	
	Thick Places	81.7	/ km	
	Neps	217.5	/ km	
Yarn Hairiness	H	3.06	%	
	CV _b	2.20	%	
Yarn Strength	Elongation	average%	6.98	%
		CV%	9.82	%
	Lea Tensile Strength	27	kg/120yd	
	Single Yarn Tensile Strength	214	gm	
	RKM	16.22	gm/tex	
Package Length		131,000	m	

Remark WAXED